

Number	20-000006-PR02 (NW-K05-02-en-02)
Owner	Soudal N.V. Everdongenlaan 18-20 2300 Turnhout Belgium
Product	Single-component polyurethane foam (in-situ foam)
Designation	Shipping name: Soudafoam PURe B1
Details	Manufacturer Soudal N.V., - Turnhout; Material Polyurethane (PUR); Density 22 kg/m ³ ; Test conditions Cut surface; Joint cross section (w x d) 20 mm x 60 mm
Special features	
Result	

Air permeability according to EN 12114:2000-03



Air permeability in new condition
 $a \leq 0,1 \text{ m}^3/(\text{m} \cdot \text{h} \cdot \text{daPa}^{2/3})$

Basis *)

DIN 18542:2009-07

*) and corresponding national versions (e.g. DIN EN)

Test report: 20-000006-PR02 PB-K05-02-en-02

Replaces ift-Nachweis:

20-000006-PR02 NW-K05-02-en-01 dated 30.04.2020.

Representation



Instructions for use

Testing of the product was determined in an "ideal" joint and in new condition based on DIN 18542, Clause 8.2 and 8.3. The results of the tested performance characteristics cannot be used as evidence of linear joints performed in practice.

Validity

There is no time limit.

When using this document the up-to-dateness of above basis and the conformity of the product have to be observed.

The data and results given relate solely to the tested/described specimen.

This test does not allow any statement to be made on further characteristics of the present structure regarding performance and quality, in particular the effects of weathering and ageing.

Notes on publication

The ift-Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies. The cover sheet can be used as abstract.

ift Rosenheim

18.06.2020



Thomas Stefan, Dipl.-Ing. (FH)
Head of Testing Department
Building Component Testing



Maximilian Denk
Operating Testing Officer
Building Component Testing

Identity-Check



www.ift-rosenheim.de/ift-geprueft
ID: CAC-599EF